

Full aliphatic polyurethane binder specially formulated for stone carpet floor application

EAN-Code
6151148962997



Options: 4kg, 20kg

Description

GardenDEC® AY-1K is Full aliphatic Polyurethane binder. Specially formulated for stone carpet floor application.

GardenDEC® AY-1K is highly hydrophobic, it does not yellow, and granules do not change color exposed to extreme sunlight. Which results in excellent resistance to mechanical, chemical, thermal, continuous water contact and extreme weather conditions. It does not yellow, and granules do not change color exposed to extreme sunlight. Which results in excellent resistance to mechanical, chemical, thermal, continuous water contact and extreme weather conditions.

GardenDEC® AY-1K It is fast curing and zero-toxic (zero V.O.C.).100% solids.

The application requires mixing 6% of the binder weight of the product with colored quartz and marble granules. If the infrastructure requires waterproofing in stone carpet applications, PoreFILLER® P-1K should be applied under the stone carpet layer.

Do not leave the packaging lid open during the application phase and the open product can be saved for the next application using the packages lid open and close method.

Important Features

- GardenDEC® AY-1K ideal for use in cold weather
- Special formulated for winter season
- Due to continuous water contact and rainwater, no lime or chlorine water stains occur
- Inhibits fungal and bacterial growth
- Highly Hydrophobic
- Highly sunlight resistance
- Full Aliphatic
- Odorless

Packaging Types 4kg 10kg 20kg

Pallet Description

| | | |
|------|--------------|-------------|
| 4kg | 125pcs X 4kg | Total 500kg |
| 10kg | 60pcs X 10kg | Total 600kg |
| 20kg | 30pcs X 20kg | Total 600kg |

Features / Benefits

- Solvent-less, 100% solids.
- Transparent, Full Aliphatic
- Fully aliphatic, no yellowing resulting from UV exposure
- Excellent resistance to heat, it will not yellow, peel or soften up to 90 °C
- Very high resistance to mechanical stresses, high tensile strength and abrasion resistance
- Excellent resistance to severe weather conditions
- Outstanding resistance to chemicals
- Outstanding hydrolysis and oxidation resistance
- Absolutely non foaming
- Comfortable application

Application Areas

- Outdoor
- Car Parks and Garages
- Squares and Parks
- Areas with a lot of car traffic
- Driveways, Terraces, Pool Sides
- Paths and walkways
- Verandas and balconies
- Outdoor recreation areas
- Ideal for pathways
- Garage ramps
- Cycle paths
- Parking areas
- Pedestrian crossings
- Secondary roads

Technical Data

Potlife : ± 35 minutes (20 °C)

Touch Drying Time : ± 3 hours (25 °C)

Drying Time : 24 hours (25 °C)

Walkable After : 12 hours

Service Temperature : (-40 °C) - (+80 °C)

QUV Accelerated Weathering Test

(6hr UV, at 70 °C (UVB-Lamps) & 6hr COND at 60 °C) - Passed 4000 hours.

Consumption

- Consumption 6% Weight of the dry granules.
- The exact ratio depends on the dust content of the granules.

Application Procedure

Clean the surface using a high pressure washer if possible.

Remove oil, grease and wax contaminants. cement laitance, loose particles, mould release agents, cured membranes must also be removed. The application surface must be dry.

Priming: Priming is required when application is on non-porous substrates, such as ceramic/glazed tiles. In this case, Primer-D 1K is used.

During the floor stone carpet application;

- For a more comfortable application, spray your trowel with a mixture of 20% glass cleaning water and 80% tap water.
- Clean your trowel frequently with Cellulosic thinner during the application phase.
- Application temperature range: +5°C to 40°C.
- Do not apply under rain or snow.
- Relative humidity must be no more than 85%.
- Try to eliminate the cured material on the walls of the mixing vessels.
- GardenDEC® AY-1K in a cool environment, avoiding exposure to direct sunlight make sure it stays under the shade provided

Technical Specifications

| PROPERTY | UNITS | METHOD | SPECIFICATION |
|--|---------|----------|----------------------|
| Viscosity (Brookfield) | cP | at 25 °C | 2,000-3,500 |
| Solids | % | - | 100 |
| Service temperature | °C | - | -40 to 80 |
| Max. temperature short time (shock) | °C | - | 200 |
| Hardness | Shore D | - | > 60 |
| Percent elongation at 23 °C | % | - | > 100 |
| QUV Accelerated Weathering Test (6hr UV, at 70 °C (UVB-Lamps) & 6hr COND at 60 °C) | - | - | passed (4,000 hours) |
| Thermal resistance (100 days at 80 °C) | - | - | passed |

Chemical (Hydrolysis) Resistance

| | | |
|--------------------------|------------------|--|
| Potassium Hydroxide, 8% | 14 days at 50 °C | no significant elastomeric property change |
| Sodium Hypochlorite, 15% | 14 days at 50 °C | no significant elastomeric property change |
| Water absorption | - | 0.5% |